



Ultra-ADA Pads Cast-in-Place (Wet-Set) Model

S P E C I F I C A T I O N S

General Information		
Material: Polyurethane Copolymer		
Sizes: 2' x 2', 2' x 3', 2' x 4', 2' x 5'		
Precautions: Product must be installed to set flush with concrete surface Product should be installed at temperatures suitable for working wet concrete		
Recommended Maintenance: Power washing approximately every six months		
Test	ASTM Test Method	Value
Weatherometer Exposure	G155-05a	200 hours – no cracks
Corrosion Resistance	B117-07	200 hours – no corrosion or change in appearance
Tensile	D412-06a	Median 2069 Elongation at break, 400%
Abrasion Resistance	D4060-07	Ave Wt Loss, L 143.7 mg Ave Wear Index, I 144
Abrasion Resistance	C-501	1000 Cycles WI 292 2000 Cycles WI 336
"Slip Test"	C-1028-07	Static Coefficient of Friction – Dry = 1.16 Static Coefficient of Friction – Wet = 1.01