



Ground Tarp Specifications

Fiber Content	100% Polypropylene
Finish	Tentered & Calendered
Construction (Approximate)	Warp: 60 Fill: 50
Weave	$\frac{3}{4}$ Basketweave
Thickness Mils , ASTM D-1777 Weight , ASTM D-3776-85	20 7.6 oz./yd.
Abrasion Resistance ASTM-D3884	Warp: 190 lbs. Fill: 250 lbs.
Tensile Strength Grab Method – ASTM D-1682	Warp: 185 lbs. Fill: 190 lbs.
Tear Strength Trapezoid Method – ASTM D-2261	Warp: 185 lbs. Fill: 190 lbs.
Burst Strength ASTM D-3786 Mullen	710 lbs./in.
Puncture Strength ASTM D-3787 Modified	165 lbs.
U.V. Resistance ASTM G-53, Retained at 5,000 hours	90%
Air Flow	230 cfm
90% closed +/- 3%	

- The above typical property values are intended as guides.
- The figures listed do not represent specification limits.